

TECHNICAL

The following table details the technical specification for Laneway.

Should you require any further information, contact Polyflor on 1800 777 425 or email technical@polyflor.com.au

Characteristics	Standards	Laneway
Gauge	ISO 24246 (EN 428)	5.0mm
Wear layer	ISO 24340 (EN 429)	0.55mm
Packaging plank size	ISO 24342 (EN 427)	12 @ 178.8 x 1219.2mm = 2.17m ² 2 @ 185 x 1505mm = 2.23m ²
Surface Treatment		PU
Total weight	ISO 23997 (EN 430)	8,000 g/m ²
General performance	ISO 10582 (EN 649)	Heterogeneous, PVC
Performance classification	ISO 10874 (EN 685)	23 / 34 / 43
Slip resistance	AS 4586 App D	R10
Chemical resistance	ISO 26987 (EN 423)	*
Residual indentation	ISO 24343-1 (EN 433)	Pass
Colour fastness to artificial light	EN ISO 105-B02	Level ≥6 (Method A)
Behaviour to fire Australian NCC	AS ISO 9239.1	Exceeds requirements
Abrasion resistance	EN 660-2 EN ISO 10582	T Type I
Castor chair (continuous use)	ISO 4918 (EN 425)	Yes / Type W
Underfloor heating	EN 1264-2	Suitable, max 27°C
Sound reduction	AS ISO 140-8	9 dB
VOC emissions	AGB/AgBB	Below quantifiable levels

* Resistant depending on concentration and time of exposure, in case of increased impact of oils, grease, acids, alkalies and other aggressive chemicals – please contact us.
Subject to changes for reasons of technical further development.

