

Polyflor Australia Fire Certificates for NCC 2022 Specification 7 C3 Compliance

Polyflors' products are manufactured and tested in the UK.

Polyflor has gone to great lengths to have the UK laboratory, Shirley Technologies Limited, Wira House BCTC, UKAS accredited to perform the fire test required by the Australian NCC, AS ISO 9239.1-2003.

In the Schedule 1 Definitions section of the NCC 2022, an Accredited Testing Laboratory means—
(a) an organisation accredited by the National Association of Testing Authorities (NATA) to undertake the relevant tests; or

(b) an organisation outside Australia accredited to undertake the relevant tests by an authority recognised by NATA through a mutual recognition agreement;

Polyflors' test certificates comply with definition (b). NATA is a signatory of ILAC (International Laboratory Accreditation Cooperation), a Mutual Recognition Program where international accreditation programs, like NATA, are recognised as similar acceptable quality standards.

UKAS is also a signatory and results obtained by a UKAS certified lab are recognised by NATA under this ILAC-MRA agreement.

The laboratory Polyflor uses, BCTC, is UKAS certified to perform AS ISO 9239.1-2003. This compliance is available via their website and is also stamped on the report.

Regarding terminology, in the definitions section of the NCC, *Critical radiant flux means the <u>critical heat</u> flux at extinguishment as determined by AS ISO 9239.1.*

The *smoke development rate* as required under Specification 7 Clause 3 is determined from the AS ISO 9239.1 test method and is by measurement of the smoke obscuration over time. This is expressed as Smoke Obscuration % x minutes.

The AS ISO test method has been copied from International Standards and hence the reason why the difference in terminology to the NCC.

The supplied fire certificate is acceptable in Australia as it is the Australian test performed by a NATA recognised certified laboratory for compliance to NCC 2022 S7C3.



Confidential Report

Our Ref: 26/03090A1/11/22







Telephone: +44 (0) 113 259 1999 Email: onestopshop@bttg.co.uk

Website: www.bttg.co.uk

Date: 20 December 2022

Our Ref: 26/03090A1/11/22

Your Ref: ---

Page: 1 of 4

Client: Polyflor Ltd

PO Box 3 Radcliffe New Road Whitefield Manchester M45 7NR

Job Title: Fire Test on One Sample of Flooring

Clients Order Ref: 2265399

Date of Receipt: 24 November 2022

Description of Sample: One sample of flooring, referenced;

Product Name Laneway
Nominal Thickness, mm: 5.0
Weight per Unit Area kg/m2 8.0
Batch No: M0119/1
Shade: 2413 Sassafras

Work Requested: We were asked to make the following test(s):

AS ISO 9239-1

* subcontracted test, UKAS accredited

** subcontracted test, EN ISO/IEC 17025 accredited

*** not UKAS accredited

ilac-MRA



Note: This report relates only to the items tested.



Telephone: +44 (0) 113 259 1999 Email: onestopshop@bttg.co.uk

Website: www.bttg.co.uk

Date: 20 December 2022

Our Ref: 26/03090A1/11/22

Your Ref:

Page: 2 of 4

Client: **Polyflor Ltd**

FIRE TESTS ACCORDING TO AS ISO 9239-1:2003

Reaction to fire tests for Floorings - Part 1: Determination of the burning behaviour using a radiant heat source (ISO 9239-1:2002)

Date of Test: 19/12/22

Conditioning

The specimens were conditioned in accordance with BS EN 13238:2010. The substrate used was a fibre cement board (ISO 390) with a thickness of (6±1)mm and a density of (1,800±200) Kg/m³ representing the standard substrate of Class A1fl or A2fl.

Mounting Method

The specimens of floor covering were tested adhered to a 6mm fibre cement backing board, as defined in BS EN 13238:2010 using Kiesel Okatmos Star 100 Adhesive.

Procedure

The test was carried out in accordance with AS ISO 9239-1:2003. The sponsor sampled and cut the specimens to the dimensions stated.

Specimens were individually placed in the combustion chamber and allowed to preheat for two minutes under a radiant panel, which gives an imposed radiant flux ranging from approximately 11.0 kW/m² to 1.0 kW/m² along the specimen.

The pilot flame used was the line burner as described and was applied to the surface of the specimen for 10 minutes and then removed.

The flame front was measured at the end of the test or at 30 minutes if applicable.

Test termination was considered to be when the flame front self extinguished or at 30 minutes, which ever is the sooner.

The heat flux from the panel incident on the specimen when self extinguished or at 30 minutes (critical heat flux CHF or HF-30) was calculated from a prior calibration.







Telephone: +44 (0) 113 259 1999 Email: onestopshop@bttg.co.uk

Website: www.bttg.co.uk

20 December 2022 Date:

26/03090A1/11/22 Our Ref: Your Ref:

> Page: 3 of 4

Client: **Polyflor Ltd**

Results

The test results relate to the behaviour of the test specimens of a material under the particular conditions of test; they are not intended to be the sole criterion for assessing the full potential fire hazard of the materials in use.

Specimen No.	<u>Direction</u> <u>of spec.</u>	Smoke Ob Develo Max %	scuration/ pment % x min	Maximum Flame front (mm)	<u>Heat Flux-30</u> (<u>HF-30)</u> (<u>kW/m²)</u>	Critical Heat/Radiant Flux (CHF/CRF) (kW/m²)	<u>Duration of</u> <u>Flaming (sec)</u>
1	Machine	62	302	151	9.9	9.9	751
2	Across	63	329	195	9.0	9.0	780
3	Across	56	299	194	9.0	9.0	720
4	Across	63	354	205	8.8	8.8	781
Mean of 3 specs.	Across	61	327	198	8.9	8.9	760
<u>Distance</u>		Time for each specimen to burn (s)					
Burnt (mm)		<u>1</u>	<u>2</u>		<u>3</u>	<u>4</u>	
50		170	163		174	205	
100		240	237		262	245	
150		360	340		480	300	
200						500	

Note

One specimen was initially tested in each direction and whichever direction gave the worst result a further two specimens were tested. Only the results of the 3 specimens in the same direction were used to calculate the mean results.







Telephone: +44 (0) 113 259 1999 Email: onestopshop@bttg.co.uk

Website: www.bttg.co.uk

Date: 20 December 2022

Our Ref: 26/03090A1/11/22

Your Ref: ---

Page: 4 of 4

Client: Polyflor Ltd

Reported by: B Marsden (Mrs), Senior laboratory Technician

Countersigned by: P Doherty Manager

Enquiries concerning this report should be addressed to Customer Services.



